



Product	Ophteis	Ophteis+
Polymer Origin	Animal origin	Animal origin
Sodium Hyaluronate Concentration	1%	1.4%
Molecular Weight (Dalton)	avg. 5 million	avg. 5 million
Zero Shear Viscosity (mPas)	avg. 1 million	avg. 3.3 million
Osmolality (mOsm/kg)	310	320
pH	6.8 - 7.6	6.8 - 7.6
Shelf Life (years)	3	3
Storage	2°C to 25°C	2°C to 25°C
Syringe Volume (ml)	0.55 / 0.85	0.55 / 0.85
Cannula Gauge (G)	27	27

Product	OphteisMAX	Methylvisc
Polymer Origin	Animal origin	Synthetic molecule
Sodium Hyaluronate Concentration	2.5%	-
HPMC Concentration	-	2.0%
Molecular Weight (Dalton)	avg. 4 million	-
Zero Shear Viscosity (mPas)	avg. 1 million	10,000 approx.
Osmolality (mOsm/kg)	360	300 to 390
pH	6.8 - 7.6	6.8 - 7.5
Shelf Life (years)	3	3
Storage	2°C to 25°C	2°C to 25°C
Syringe Volume (ml)	0.85	2
Cannula Gauge (G)	25	23

